

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Publication number:

0 078 597
A2

12

EUROPEAN PATENT APPLICATION

21 Application number: 82304259.3

51 Int. Cl.³: A 61 K 7/11

22 Date of filing: 12.08.82

30 Priority: 29.10.81 JP 173253/81

71 Applicant: Toray Silicone Company Limited,
2-8 Nihonbashi Muromachi, Chuo-ku Tokyo 103 (JP)

43 Date of publication of application: 11.05.83
Bulletin 83/19

72 Inventor: Ona, Isao, 2848-46, Kubota Sodegaura-machi,
Kimitsu-gun Chiba-ken (JP)
Inventor: Ozaki, Masaru, Nishi 1-6 Yushudai Ichihara-shi,
Chiba-ken (JP)
Inventor: Harashima, Asao, Nishi 1-6 Yushudai
Ichihara-shi, Chiba-ken (JP)
Inventor: Taki, Yoichiro, Nishi 1-6 Yushudai Ichihara-shi,
Chiba-ken (JP)

84 Designated Contracting States: DE FR GB IT

74 Representative: Lewin, John Harvey et al, Elkington and
Fife High Holborn House 52/54 High Holborn, London
WC1V 6SH (GB)

54 Composition used to groom hair.

57 A composition, used to groom hair, consisting essentially of an organopolysiloxane having at least one alkyl-amino substituent and at least one substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, said organopolysiloxane having a viscosity range of to 100,000 centistokes at 25 °C, is disclosed.

EP 0 078 597 A2

COMPOSITION USED TO GROOM HAIR

This invention relates to a composition, used to groom hair, consisting essentially of an organopolysiloxane having at least one alkylamino substituent and at least one substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, said organopolysiloxane having a viscosity range of 1 to 100,000 centistokes at 25°C.

Hair is easily damaged mechanically by combing, brushing, and washing. Hair is also easily damaged physically and chemically by the sun, hair dryers, and permanents. In order to protect the hair, vegetable oils such as camellia oil and olive oil, animal oils such as lanolin and beef tallow, mineral oils such as vaseline and paraffin, and synthetic oils have been used either directly, as emulsions, or dissolved in solvents.

In recent years, organopolysiloxane has attracted attention as a hair grooming agent because it gives hair glossiness, suppleness, smoothness, and a moist feeling. For example, a hair dressing composed of dimethylpolysiloxane and diol derivatives or a branched aliphatic alcohol is disclosed in U.S. Patent Number 4,243,657; a hair conditioning composition composed of a polyorganosiloxane-polyoxyalkylene block copolymer and aqueous or anhydrous ethanol is disclosed in Japanese Patent Sho 56[1980]-136214; a hair grooming agent composed of (alkylamino)methylpolysiloxane and a cationic surfactant with an aqueous carrier is

disclosed in Great Britain Patent Number 2,058,103; and a dressing which uses a cationic modified organopolysiloxane containing quaternary nitrogen is disclosed in Japanese Patent Sho 55[1980]-66506.

Hair grooming agents in which dimethylpolysiloxane is used has the drawback, however, in that dust tends to stick to the hair and the flying phenomenon easily occurs because of the generation of static electricity. Those in which organopolysiloxane-polyoxyalkylene block copolymers are used are able to prevent the generation of static electricity, but have the drawbacks that they are easily removed when swimming or washing the hair because they are easily dissolved in water. Those in which (alkylamino)methylpolysiloxane is used are ideal in terms of their durability, but have the drawback that static electricity is easily generated. Those in which cationic modified organopolysiloxane containing quaternary nitrogen is used are fairly good in both their durability and antistatic properties, but have the drawback in that those qualities alone are insufficient. Thus, in the case of conventional hair grooming agents, even though they generally succeed in giving glossiness, suppleness, smoothness, and a moist feeling, they have problems with durability and antistatic properties, so a grooming agent in which the treatment effects, the durability, and the antistatic properties are fully satisfactory, has not yet been obtained.

As a result of intensive investigations to improve the above-mentioned drawbacks, the present inventors have succeeded in developing a hair grooming agent which gives the hair an excellent glossiness,

suppleness, smoothness, and moist feeling, making it easy to brush and providing it with antistatic properties, and which moreover has a durability that can make the treatment effects adequately durable because it is adsorbed onto the hair.

That is, the present invention relates to a composition, used to groom hair, characterized in that it consists essentially of an organopolysiloxane having at least one alkylamino substituent and at least one substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, said organopolysiloxane having a viscosity range of 1 to 100,000 centistokes at 25°C.

It is thus an object of this invention to provide a composition used for grooming hair which is adsorbed onto the hair and which gives it a durable gloss, suppleness, smoothness, and a moist feeling, making it easy to brush and providing it with antistatic properties.


Detailed Description

This invention relates to a composition, used to groom hair, consisting essentially of an organopolysiloxane having at least one alkylamino substituent and at least one substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, said organopolysiloxane having a viscosity range of 1 to 100,000 centistokes at 25°C.

It is believed that the organopolysiloxane imparts glossiness, suppleness, smoothness, and a moist feeling onto the hair. The molecular configuration of the organopolysiloxane is not

critical for the purpose of this invention and therefore may be either a straight chain, a branched chain, a cyclic, or a branched chain network. It is preferred, however, that the configuration be a straight chain.


By means of the alkylamino groups bonded to the silicon atoms which firmly adsorbs on the hair, it is believed that durability is achieved. It is essential that the organopolysiloxane have at least one alkylamino substituent in order to achieve this durability. A suitable example of the alkylamino groups is represented by the general formula



wherein R' is a divalent hydrocarbon group, R^2 and R^3 are selected from the group consisting of hydrogen and monovalent hydrocarbon groups, and a has a value of 0 to 5. Examples of the divalent hydrocarbon group, R' , include alkylene groups such as methylene, ethylene, propylene, isobutylene and butylene, and alkylenearylene groups such as $-(CH_2)_2-C_6H_4-$. It is preferred that R' be an alkylene group, with propylene being the most preferred. Examples of the monovalent hydrocarbon groups, R^2 and R^3 , are alkyl groups such as methyl, ethyl, propyl, and hexyl, and aryl groups such as phenyl. It is further preferred that a have a value of 0 to 1.

It is believed that the organopolysiloxane substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups prevents the generation of static electricity and bestows wettability, due to their hydrophilic character. A suitable example of the oxyalkylene and

polyoxyalkylene groups is represented by the general formula



wherein R^4 is a divalent hydrocarbon group, R^5 is selected from the group consisting of hydrogen and end-blocking groups, b has a value of 0 to 1, m has a value of 1 to 5 and c has a value of 1 to 100. Examples of the divalent hydrocarbon group, R^4 , include alkylene groups such as methylene, ethylene, propylene, isobutylene and butylene, and alkylenearylene groups such as $-(CH_2)_2-C_6H_4-$. It is preferred that R^4 be an alkylene group. The end-blocking group, R^5 , is represented by monovalent hydrocarbons, acyls, and, carbonic acid monoester groups. Specific examples of the monovalent hydrocarbon group include alkyl groups such as methyl, ethyl, hexyl, and propyl, and aryl groups such as phenyl. The acyl group is represented by the acetyl, propionyl, and benzoyl groups. It is preferred that b have the value of 1, m have the value of 2 to 3, and c have the value of 3 to 70. A suitable example of the hydroxyalkyl group is expressed by the general formula $-R^4OH$ wherein R^4 is a divalent hydrocarbon group. Examples of the divalent hydrocarbon group, R^4 , include alkylene groups such as methylene, ethylene, propylene, isobutylene and butylene, and alkylenearylene groups such as $-(CH_2)_2-C_6H_4-$. It is preferred that R^4 be an alkylene group. It is further preferred that the organopolysiloxane substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, be a

polyoxyalkylene, with the second preference being oxyalkylene, and the third, hydroxyalkyl.

Groups other than those mentioned above which constitutes the organopolysiloxane include alkyl groups such as methyl, ethyl, propyl, octyl, and dodecyl groups, aryl groups such as phenyl and tolyl groups, cycloalkyl groups such as cyclohexyl and cycloheptyl groups, and substituted alkyl groups such as 2-phenyl-ethyl, 3,3,3-trifluoropropyl, and 3-chloropropyl groups. Among these, the methyl group is the most common. Hydroxyl and alkoxy groups which are directly attached to the silicon atoms may also be present.

The organopolysiloxane of the present invention can be prepared by techniques well known to those skilled in the art. A suitable method is one of reacting an organopolysiloxane which contains alkylamino groups with an organopolysiloxane which contains oxyalkylene, polyoxyalkylene, or hydroxyalkyl groups in the presence of an alkaline catalyst. Another method is reacting ammonia or an alkylamine with an organopolysiloxane which contains oxyalkylene, polyoxyalkylene, or hydroxyalkyl groups as well as monohalogenated alkyl groups. A further method is the condensation reaction of a dialkoxysilane containing aminoalkyl groups with a dialkoxysilane containing oxyalkylene, polyoxyalkylene, or hydroxyalkyl groups in the presence of a silanol endblocked diorganopolysiloxane.

The quantity of the organopolysiloxane of the present employed used, will vary according to its intended application, but is usually employed in the range of 0.01 to 10 percent by weight with respect to

the total quantity of the hair care agent. The organopolysiloxane can be used as is, dissolved in an aqueous solution or an organic solvent, or employed as an emulsion. Besides the organopolysiloxane, the hair care agent may also contain additives used in cosmetics and sprays. Conventional cosmetic additives include surfactants; organic solvents such as alcohols, esters, ketones, and aromatics; perfumes; inorganic pigments; coloring agents; thickeners; animal fats and oils; vegetable fats and oils; mineral fats and oils; ultraviolet ray absorbants; antioxidants; antiseptics; appearance-changing additives; and other organopolysiloxanes. Conventional spray additives includes spray agents such as LPG, trichloromonofluoromethane, dichlorodifluoromethane, dichlorotetrafluoroethane and carbonic acid gas.

The organopolysiloxane of the present invention can be used in shampoos, rinses, hair cremes, hair oils, hair lotions, liquid or solid pomades, stick pomades, shaving foams, and skin ointments such as skin creams, shaving creams, and skin lotions.

Hair, as used in the present invention, refers to the hair of the head, other human hair, artificial hair such as wigs, and animal hair such as that of dogs, cats and sheep.


Now in order that those skilled in the art may better understand the invention, the following examples are given by way of illustration and not by way of limitation. All parts referred to herein are by weight, and all viscosities are measured at 25°C, unless otherwise specified.

Example 1


Hair grooming agents were prepared and evaluated on hair in terms of imparting glossiness, suppleness, smoothness, moist feeling, ease of brushing, and difficulty of dust adhesion. The hair grooming agent consists of 4 parts by weight of an organopolysiloxane, 16 parts by weight of ethanol, a small amount of artificial perfume, 40 parts by weight of trichloromonofluoromethane, and 40 parts by weight of dichlorodifluoromethane. The agent is then placed in an aerosol-type spray can and sprayed uniformly onto the hair of a woman's head, having a hair length of about 25 centimeters. The hair was brushed 100 times with a brush made of polyethylene, and the ease of brushing, glossiness, suppleness, smoothness, and moist feeling were evaluated by means of a sensory inspection. The reporting system of the evaluation was a scale of 1 to 4 with 1 being extremely good, 2 being fairly good, 3 being fairly poor, and 4 being extremely poor. The ease with which dust stuck to the hair immediately after brushing, due to the generation of static electricity, was also evaluated. This was done by preparing a large number of very small pieces of paper, blowing them on the hair immediately after brushing, and evaluating according to the number of pieces of paper absorbed onto the hair. The evaluation scale was also 1 to 4, with 1 indicating almost no adhesion, 2, some adhesion, 3, moderate adhesion, and 4 abundant adhesion.

The organopolysiloxanes of the present invention used in the hair grooming agent are as follows:


Composition 1, having a viscosity of 4000 centistokes at 25°C:



Composition 2, having a viscosity of 400 centistokes at 25°C:




Composition 3, having a viscosity of 200 centistokes at 25°C:




Organopolysiloxanes, serving as comparisons, used in the hair grooming agent are as follows:


Comparison Composition 1, having a viscosity of 100 centistokes at 25°C:



Comparison Composition 2, having a viscosity of 1100 centistokes at 25°C:



and Comparison Composition 3, having a viscosity of 350 centistokes at 25°C:



The results are as follows:

Item

	Composition			Comparison Composition		
	1	2	3	1	2	3
Glossiness	1	1	1	2	1	2
Suppleness	1	1	1	2	2	2
Smoothness	1	1	1	1	3	1
Moist Feeling	1	1	1	3	3	1
Ease of Brushing	1	1	2	3	3	2
Difficulty of Dust Adhesion	1	2	2	4	4	1


As shown in the above results, it was found that the organopolysiloxanes of the present invention were considerably superior to the conventionally well known organopolysiloxanes which were used in the comparison compositions. In the present invention, it is clear that the polyoxyalkylene substituent is superior to the oxyalkylene substituent which is superior to the hydroxyalkyl substituent, as shown in the results in ease of brushing and difficulty of dust adhesion. Though Comparison Composition 3 is not greatly different from those of the present invention, as shown in the results, it is extremely inferior to the present invention in terms of durability as shown in Example 2.

Example 2

The durability of organopolysiloxanes in hair grooming agents was tested by immersing 20 grams of a lock of woman's hair, approximately 15 centimeters in length, in a hair grooming agent consisting of 4 parts by weight of an organopolysiloxane, and 96 parts by weight of n-pentane. After a 30 minute immersion, the hair was


removed, and after it ceased dripping, was dried with a hair dryer. This lock of hair was then washed while being lightly massaged for 15 minutes in a 0.1 percent by weight aqueous solution of potassium soap used for babies which had been warmed to 45°C. The hair was then rinsed with water and dried. The quantity of organopolysiloxane adhering after shampooing was measured using an X-ray fluorescence apparatus manufactured by Rigaku Denki Kogyo. The quantity adhering was expressed as an organopolysiloxane residue ratio with the quantity adhering before shampooing regarded as 100. Sensory inspection and evaluation before and after shampooing was carried out in the same manner as in Example 1.

The organopolysiloxane of the present invention used in the hair grooming agent is: Composition 4, having a viscosity of 8500 centistokes at 25°C:




Organopolysiloxanes, serving as comparisons, used in the hair grooming agent are as follows:

Comparison Composition 4, having a viscosity of 100 centistokes at 25°C:



and Comparison Composition 5, having a viscosity of 350 centistokes at 25°C.



The results are as follows:

Item	Composition	Comparison Composition	
	4	4	5
<u>Before shampooing</u>			
Glossiness	1	2	2
Suppleness	1	2	2
Smoothness	1	1	1
Moist Feeling	1	3	1
<u>After shampooing</u>			
Glossiness	1	3	4
Suppleness	2	3	3
Smoothness	1	3	4
Moist Feeling	2	4	4
Organopolysiloxane Residue Ratio (%)	38	11	4


It was found that the organopolysiloxane of the present invention, as indicated by Composition 4, had a high ratio of organopolysiloxane remaining, even after shampooing 3 times, because it was firmly adsorbed onto the hair, and consequently its effects upon the hair were retained, imparting an excellent durability. By contrast, the effects on the hair before washing in the case of Comparison Composition 5 were not greatly different from the present invention, but its effects upon the hair after shampooing largely disappeared, and its durability was inferior.

CLAIMS:

1. A composition used to groom hair consisting essentially of an organopolysiloxane having at least one alkylamino substituent and at least one substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, said organopolysiloxane having a viscosity range of 1 to 100,000 centistokes at 25°C.

2. A composition used to groom hair as defined in Claim 1 wherein the organopolysiloxane has at least one alkylamino substituent and at least one polyoxyalkylene substituent, said organopolysiloxane having a viscosity range of 5 to 10,000 centistokes at 25°C and being a straight chain.

3. A composition used to groom hair as defined in Claim 2 wherein the alkylamino substituent has the general formula



wherein R' is a divalent hydrocarbon group,
 R^2 and R^3 are selected from the group
 consisting
 of hydrogen and monovalent hydrocarbon
 groups, and

a has a value of 0 to 5,
 and the polyoxyalkylene substituent has the
 general
 formula

$$-(R^4)_b - C - (C_m H_{2m} O)_c - R^5$$

wherein R^4 is a divalent hydrocarbon group.
 R^5 is selected from the group consisting
 of

hydrogen and end-blocking groups,
 b has a value of 0 to 1,
 m has a value of 1 to 5, and
 c has a value of 1 to 100.

4. A composition used to groom hair as defined in Claim 3 wherein R' is an alkylene group, a has a value of 0 to 1, R^4 is an alkylene group, b is 1, m has a value of 2 to 3, and c has a value of 3 to 70.

5. A composition used to groom hair as defined in Claim 4 wherein R' is propylene.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 078 597
A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 82304259.3

(51) Int. Cl.³: **A 61 K 7/11**
C 08 L 83/08, C 08 L 83/12

(22) Date of filing: 12.08.82

(30) Priority: 29.10.81 JP 173253/81

(43) Date of publication of application:
11.05.83 Bulletin 83/19

(88) Date of deferred publication of search report: 01.02.84

(84) Designated Contracting States:
DE FR GB IT

(71) Applicant: Toray Silicone Company Limited
2-8 Nihonbashi Muromachi
Chuo-ku Tokyo 103(JP)

(72) Inventor: Ona, Isao
2848-46, Kubota Sodegaura-machi
Kimitsu-gun Chiba-ken(JP)

(72) Inventor: Ozaki, Masaru
Nishi 1-6 Yushudai Ichihara-shi
Chiba-ken(JP)

(72) Inventor: Harashima, Asao
Nishi 1-6 Yushudai Ichihara-shi
Chiba-ken(JP)

(72) Inventor: Taki, Yoichiro
Nishi 1-6 Yushudai Ichihara-shi
Chiba-ken(JP)

(74) Representative: Lewin, John Harvey et al,
Elkington and Fife High Holborn House 52/54 High
Holborn
London WC1V 6SH(GB)

(54) Composition used to groom hair.

(57) A composition, used to groom hair, consisting essentially of an organopolysiloxane having at least one alkylamino substituent and at least one substituent selected from the group consisting of oxyalkylene, polyoxyalkylene, and hydroxyalkyl groups, said organopolysiloxane having a viscosity range of 1 to 100,000 centistokes at 25°C, is disclosed.



European Patent
Office

EUROPEAN SEARCH REPORT

0078597

Application number

EP 82 30 4259

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
X	CHEMICAL ABSTRACTS, vol. 88, no. 6, 6 février 1978, page 63, no. 39010v, Columbus, Ohio, USA & JP - A - 77 103 498 (SHIN-ETSU CHEMICAL INDUSTRY CO., LTD.) 30-08-1977 * Abstract *	1-5	A 61 K 7/11 C 08 L 83/08 C 08 L 83/12
X	GB-A-1 409 742 (ICI) * Example 7 *	1	
Y	FR-A-1 355 136 (BAYER) * Example 5 *	1	
Y	US-A-3 549 590 (HOLDSTOCK et al.) * Claims 1-4; column 1, lines 60-66 *	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 3)
			C 08 L 83/00 C 08 G 77/00 A 61 K 7/00 D 06 M 15/00
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 02-11-1983	Examiner WILLEKENS G.E.J.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure D : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			